



Proud Member and Participant of:
 443 Bricker Road Bernville, PA 19506
www.eastcoasterosion.com
 1.800.582.4005 +1.610.488.8496 Fax +1.610.488.8494



Material and Performance Specification

EC-7Y COIR MAT

Description: Coir fiber is obtained from the bristles of the outer layer of the fruit of the Coconut tree and is 100% biodegradable. Coir Mats are woven with coir fiber yarns providing strength, environmental friendliness and functional longevity in excess of three years. EC-7Y meet the Type 4.A, specifications established by the Erosion Control Technology Council (ECTC) and also meets the Federal Highway Administration’s (FHWA) FP-03 Section 713.17.

Material: Coconut Fiber

Roll Size

Width:	6.5 ft (2 m)
Length:	167 ft (50 m)
Area:	120 yd ² (100 m ²)
Weight +10%:	24 oz/yd ² (814 g/m ²)

Design Value Properties

Property	
Shear Stress	4.50 lbs/ft ² (215 Pa)
Velocity	12.0 ft/s (3.66 m/s)
C Factor	0.003
Open Area – Calculated	41%
Net Opening	5/8" (15 mm) x 1/2" (12 mm)

Index Value Properties

Property	Test Method	Value
Mass/Unit Area	ASTM D5261	22.3 oz/yd ² (757.0 g/m ²)
Thickness	ASTM D5199	0.36 in. (9.1 mm)
Light Penetration	ASTM D6567	33%
Dry Tensile Strength-MD	ASTM D4595/ASTM D6818*	1600 lb/ft (23.4 kN/m)
Dry Elongation-MD	ASTM D4595/ASTM D6818*	27%
Dry Tensile Strength-TD	ASTM D4595/ASTM D6818*	1310 lb/ft (19.2 kN/m)
Dry Elongation-TD	ASTM D4595/ASTM D6818*	27%
Wet Tensile Strength-MD	ASTM D4595	1455 lb/ft (21.3 kN/m)
Wet Elongation-MD	ASTM D4595	27%
Wet Tensile Strength-TD	ASTM D4595	1425 lb/ft (20.8 kN/m)
Wet Elongation-TD	ASTM D4595	27%

*Both ASTM D4595 and D6818 are used to test tensile strength. ASTM D6818 is preferred in erosion control applications.

Primary Usage

Slopes	2:1	1:1	>1:1
--------	-----	-----	------

The values presented are for guidance purposes and do not constitute the practice of engineering. East Coast Erosion Blankets LLC (ECEB) ascertains that at the time of manufacture, all information presented herein is accurate and reliable and falls within the ECEB manufacturing product specification variances. If the product does not meet the stated values and ECEB is notified in writing prior to installation, the product will be replaced at no cost to the purchaser. ECEB will not be held liable for any type of damage or losses, directly, or indirectly for failure of this product. Current revision supersedes all previous versions for this product.