

Proud Member and Participant of: www.eastcoasterosion.com 443 Bricker Road Bernville, PA 19506 1.800.582.4005 +1.610.488.8496 Fax +1.610.488.8494

Material and Performance Specification

ECP-2 10 oz.[™] Polypropylene Turf Reinforcement Mat

Description:

The ECP-2 10 oz^m is made with uniformly distributed 100% polypropylene fiber and two medium weight polypropylene nets securely sewn together with UV stabilized thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECP-2 10 oz^m is a permanent turf reinforcement mat and is suitable for 1:1 slopes and high-flow channels. The ECP-2 10 oz^m meets Type 5.A, 5.B & 5.C specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.18.

Matrix:		1	2	
	Green or Tan F	Polypropylene Fiber	N/A	
Netting:		Туре		Net Color
Top:	Medium weight 5# PM	ISF UV Stabilized Polypr	opylene	Black
Middle:	None			
Bottom:	Medium weight 5# PM	ISF UV Stabilized Polypr	opylene	
Net Opening:		Тор	Middle	Bottom
	0.5	5" x 0.5"	N/A	0.5" x 0.5"
Thread:		Туре	Color	
	UV Stabili	zed Thread	Black	
Roll Sizes:	St	andard	"A" Size	Mega
Width:	8 ft	2.4 m	4.00 ft 1.2 m	16 ft 4.9 m
Length:	112.5 ft	34.3 m	225 ft 68.6 m	112.5 ft 34.3 m
Weight:*	62 lbs	28.1 kg	62 lbs 28.1 kg	124 lbs 56.2 kg
Area:	100 yd ²	83.6 m ²	100 yd ² 83.6 m ²	200 yd ² 167.2 m ²
#/Pallet:		16	9	16

*Weight at time of manufacturing within specified tolerances.

Property	Test Method		Ту	Typical		
Mass/Unit Area	ASTM D6566	10.00 o	z/yd²	339.1	g/m2	
Thickness	ASTM D6525	0.40 in	ı	10.16	mm	
Tensile Strength-MD	ASTM D6818	370 lb	o/ft	5.40	kN/m	
Elongation-MD	ASTM D6818	24 %	, 5			
Tensile Strength-TD	ASTM D6818	315 ^{lb}	o/ft	4.60	kN/m	
Elongation-TD	ASTM D6818	20.0 %				
Light Penetration	ASTM D6567	25 %	, b			
Density / Specific Gravity	ASTM D792	0.917 g	/cm³			
Water Absorption	ASTM D1117	0 %	, b			
Resiliency	ASTM D6524	80 %	Ś			
UV Resistance	ASTM D4355	82 %	Ś	1000	hours	

*May differ depending upon raw material variations

Slope Perf	ormance Design Values*:	

Property	Test Method		Value	
C-Factors	ASTM D6459		0.01	
Slope Length (L)	≤ 3:1	3:1-2:1	≥ 2:1	
< 50 ft (15 m)	0.005	0.012	0.058	
50 ft – 100 ft	0.012	0.025	0.062	
>100 ft (30 m)	0.020	0.036	0.071	

*Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Test Method	Parameters	Results	
	50mm (2in) / hr-30 min	SLR**=4.58	
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=8.80	
	150mm (6in) / hr-30 min	SLR**=16.92	
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.42 lb/ft ²	
ECTC Method 4 Germination To	p soil; Fescue; 21 day incub	ation 482 %	

**Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor

***The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Property	Test Method		Valu		
Unvegetated Shear Stress	ASTM D 6460	2.30	lbs/ft ²	110.12	Ра
Unvegetated Velocity	ASTM D 6460	9.0	ft/s	2.74	m/s
Vegetated Shear Stress	ASTM D 6460	10.0	lbs/ft ²	478.80	Ра
Vegetated Velocity	ASTM D 6460	18.0	ft/s	5.49	m/s
Manning's N (Value Represents a Range)			0.02	24	
*Large-Scale Results obtain Laboratory	ed by 3 rd Party GA	I Accred	ited Inde	pendent	

The values presented are for guidance purposes and do not constitute the practice of engineering. East Coast Erosion Blankets LLC (ECEB) ascertains that at the time of manufacture, all information presented herein is accurate and reliable and falls within the ECEB manufacturing product specification variances. If the product does not meet the stated values and ECEB is notified in writing prior to installation, the product will be replaced at no cost to the purchaser. ECEB will not be held liable for any type of damage or losses. directly, or indirectly for failure of this product. Current revision supersedes all previous versions for this product.